

LUBRIONE™
INTERNALLY LUBRICATED
FORMULATIONS

LubriOne™ Internally Lubricated Formulations

PRODUCT DESCRIPTION	UNITS	TEST METHOD	NN-000/15T BLACK	NN-20GF-10GB/13T-2S BLACK	NN-30GF/10T WHITE	LB8900-0001 30GF/15T NATURAL
Base Polymer			PA 66	PA 66	PA 66	PK
General Properties						
Specific Gravity	g/cm ³	ASTM D792	1.23	1.46	1.47	1.56
Molding Shrinkage		ASTM D955				
Flow	%		1.0–2.0	0.20–0.50	0.50–1.0	0.30–0.60
Water Absorption (23°C, 24 hr.)	%	ASTM D570	0.8	–	0.050–1.0	0.3
Mechanical Properties						
Tensile Modulus ⁽¹⁾	MPa	ASTM D638	2650	9650	9790	8050
Tensile Strength ⁽¹⁾ (Yield)	MPa	ASTM D638	61.4	119	122	119
Tensile Elongation ⁽¹⁾ (Break)	%	ASTM D638	3.0–5.0	1.0–3.0	1.5	3
Flexural Modulus	MPa	ASTM D790	2760	6890	6890	7380
Flexural Strength	MPa	ASTM D790	108	172	214	182
Coefficient of Friction		ASTM D1894				
vs. Steel – Dynamic			0.43	0.59	0.14	0.10
vs. Steel – Static			0.25	0.46	0.18	0.15
Impact						
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	J/m	ASTM D256A	41	64 ⁽⁶⁾	110	107
Thermal Properties						
Heat Deflection Temperature		ASTM D648				
0.45 MPa	°C		215 ⁽⁶⁾	–	250	215
1.8 MPa	°C		65 ⁽⁶⁾	239 ⁽⁷⁾	244 ⁽⁶⁾	210
Electrical Properties						
Surface Resistivity	ohms/sq	ASTM D254	–	–	–	1.30x10 ¹²
Dielectric Strength (Short Time)	kV/mm		–	–	8.5	–
Flammability						
Flame Rating	Class	UL 94	HB	–	–	HB

NOTES (1) Type I, 5.1mm/min
(2) Type I, 21.3 mm/min

(3) Type I, 50 mm/min
(4) Type I, 5.1mm/min, Break

(5) 3.2 mm thick, Unannealed
(6) 6.35 mm thick, Unannealed

(7) 3.2 mm thick, Annealed

LB8900-0002 30GF/13T-2S NATURAL	LB8900-0003 18T-2S NATURAL	ATT-000/5T BLACK	AT-000/18T- 2S NATURAL	5209 FPL 20 NATURAL	PS-30GF/2S NATURAL	LB5210-0237 1B NATURAL	PC-10CF/15T BLACK
PK	PK	POM	POM	POM	PBT	PP	PC
1.55	1.33	1.38	1.47	1.51	1.54	1.13	1.31
0.20-0.40	1.7-2.3	1.5-2.0	2.0-3.0	2.0-3.0	0.20-0.40	0.10-0.30	0.10-0.30
0.4	0.4	0.050	-	0.050	-	-	-
7380	1250	965	1770	2420	8620	4140	-
94	47	35	40	45	108	72.4	90
2	35	40	30	26	3	-	-
6410	1300	1080	1740	1790	6690	4840	5500
167	55	41.4	62.7	68.3	165	110	130
0.11	0.12	0.12	0.10	0.12	0.14	0.16	0.14
0.12	0.19	0.11	0.14	0.13	0.24	0.17	0.17
107	70	80	37	37	75	-	69
216	184	152	151 ⁽⁶⁾	153 ⁽⁶⁾	218 ⁽⁶⁾	-	-
210	75	94	81.1 ⁽⁶⁾	88	197 ⁽⁶⁾	-	135 ⁽⁵⁾
1.9x10 ¹²	5.2x10 ¹²	-	-	-	-	-	1.0x10 ⁹
-	-	-	-	-	-	-	-
HB	HB	-	HB	-	-	-	-

LubriOne™ Internally Lubricated Formulations - Non-PFAS

PRODUCT DESCRIPTION	UNITS	TEST METHOD	LB6000-5024 RS HI Natural	LB6000-5021 RS S1 Black	LB6000-5021 RS X2 Black	LB6000-5019 X1 Black	LB6700-5001 RS AF Black	
Base Polymer			PA 6				PA6/PA66	
Lubricant			UHMWPE ¹	UHMWPE	UHMWPE	UHMWPE	UHMWPE	
Filler type			GF10	GF30	GF30	GF50	GF50	
General Properties								
Specific Gravity	g/cm ³	ISO 1183	1.18	1.35	1.39	1.55	1.58	
Mechanical Properties								
Tensile Modulus (23°C)	MPa	ISO 527-1	4250	9500	9000	15500	16600	
Tensile Strength (Yield, 23°C)	MPa	ISO-527-2	97	150	160	205	200	
Tensile Elongation (Break, 23°C)	%	ISO-527-2	12	2.5	3	2.7	2.4	
Flexural Strength (23°C)	MPa	ISO 178	103	-	-	285	265	
Flexural Modulus (23°C)	MPa	ISO 178	3250	-	-	12400	11100	
Impact								
Charpy Notched Impact Strength (23°C, Injection Molded)	kJ/m ²	ISO 179	14	12	10	15	10	
Charpy Unnotched Impact Strength (23°C, Injection Molded)	kJ/m ²	ISO 179	82	55	61	75	60	
Thermal Properties								
Deflection Temperature Under Load 1.8 Mpa, Unannealed	°C	ISO 75-2/A	107	-	-	204	-	
Coefficient of Friction (CoF) & Wear Rate								
CoF vs. Steel - Dynamic		ASTM D1894	-	0.212	0.186	-	-	
CoF vs. Steel - Static		ASTM D1894	-	0.237	0.183	-	-	
CoF (20min 0.2 m/s)	g/min	ASTM G77	-	-	-	-	-	
Wear Rate (20h, 1m/s)	g/min	ASTM G77	-	-	-	-	-	
Wear Rate (PV=2500)	(in3-min/ ft-lb-hr) *10 ⁻¹⁰	ASTM D3702	-	125	175	-	-	
Flammability								
Flame Rating		UL 94	-	-	-	-	-	

NOTES *ASTM D3702 (PV=2500, against 1018-steel)
¹UHMWPE - ultra high molecular weight polyethylene
²MoS₂ - molybdenum disulphide

NN-000/01M Black SO	REC LB6600- 5030 RS Grey	LB3300- 5010 RS Natural	LB3300- 5005 RS Natural	REC LB3220- 5001 RS C Natural X1	LB8900- 5010 GP Grey	LB8900- 5006 RS PE Natural	LB8900- 5004 RS PE Natural	LB4200- 5022 Black	LB4200- 5023 Natural
PA66		PBT		PC	PKE			POM	
MoS2 ²	Graphite	UHMWPE	UHMWPE	UHMWPE	Graphite	UHMWPE	UHMWPE	MoS2	UHMWPE
Unfilled	GF33	GF20	MI20	GF10	Unfilled	GF20	GF30	Unfilled	Unfilled
1.14	1.44	1.42	1.46	1.23	1.26	1.34	1.43	1.4	1.35
3500	10600	6300	3330	4000	1630	5300	9250	2470	2150
85	164	102	55	60	60	108	99.1	55	50
3.4	2.0	4.2	8	2.5	46	3.7	1.5	11	11
108	215	127	78	85	38	155	117	73	68
2690	9000	4700	3000	3100	1380	4600	5450	2210	2070
3	6	7.7	4.3	12	15	10	7.6	8	5
65	50	47	69	-	NB	63	36	NB	NB
73	235	-	-	-	90	210	204	86	80
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	0.79	0.79	-	-
-	-	-	-	-	-	1.02E-05	1.89E-05	-	-
-	-	-	-	-	-	-	-	-	-
-	-	HB	HB	V2 @ 3mm	-	-	-	-	-



EXPLORE WEAR RESISTANCE

LubriOne internally lubricated thermoplastic polymers have been specifically designed to improve tribological performance in components, offering low coefficient of friction and improved wear-resistance properties. These properties, coupled with a wide array of base engineering thermoplastics, deliver the distinct benefits of LubriOne:

- Reduced friction and heat buildup between interacting surfaces
- Reduced noise and vibration among components in relative motion
- Reduced weight and improved design freedom
- Lower long-term maintenance costs when grease and other lubricants are eliminated

To learn more about LubriOne™ internally lubricated solutions, contact Avient at +1.844.4AVIENT (1.844.428.4368)

www.avient.com



Copyright © 2023, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.